



## C.A.S. Paper Mill Co., Ltd Singburi Mill Technical Specification

Printing method : coldset web offset

		High Brightness 62	High Brightness 74	High Brightness 74
<b>Brand</b>		<b>CAS Bright 62</b>	<b>CAS Bright 74</b>	<b>CAS Bright 74</b>
<b>Substance Weight</b>	g/m <sup>2</sup>	48.8±1	48.8±1	55±2
<b>Thickness</b>	Micron	67±5	67±5	67±5
<b>Brightness</b>	% ISO	62±2	74±2	74±2
<b>Opacity</b>	%	≥90	≥90	≥90
<b>Moisture Content</b>	%	8.8±1	8.8±1	8.8±1
<b>Reel Diameter</b>	mm	1,000 (±30)	1,000 (±30)	1,000 (±30)
<b>Core Inside Diameter</b>	mm	76±1	76±1	76±1
<b>Core Outside Diameter</b>	mm	106±1	106±1	106±1
<b>Core Length Tolerance</b>	mm	±4	±4	±4
<b>Reel Width Tolerance</b>	mm	±2	±2	±2
<b>Reel Width Availability</b>	mm	340 - 1905	340 - 1905	340 - 1905

**C.A.S. Paper Mill Co., Ltd.** has given crucial importance to the environment and public health and safety,  
the mill was awarded with the ISO9001:2008, ISO14001:2004, and OHSAS18001:2007

